

Enviro-Syn<sup>®</sup> HCR-7000-WL<sup>®</sup> is part of the proprietary, eco-friendly Modified Acid<sup>™</sup> product portfolio that minimizes the hazardous exposure levels, corrosion rates and negative HSE properties of hydrochloric acid (HCl), while maintaining the positive aspects of solubilizing ability and reactivity rates. Enviro-Syn HCR-7000-WL is a strong modified acid that in concentrate has similar solubilizing abilities as 15% HCl and can be enhanced through the addition of conventional oilfield chemistry. Enviro-Syn HCR-7000-WL is typically deployed at 50% (1:1 HCR:water), 33% (1:2 HCR:water) or 20% (1:4 HCR:water) concentration to provide exceptional value and reduce transportation/storage costs.

Fluid's wireline compatible blends enable operators to spot acid with perforating bottom hole assemblies (BHAs) saving substantial amounts of water and time in hydraulic fracturing operations (patented formulas and methods). High spent pH stability, and the calcium- and iron-coordinating effects of Enviro-Syn HCR-7000-WL reduces the precipitation issues prevalent with HCl. This will minimize or eliminate formation damage that can occur when using HCl as a spearhead acid and assist with effluent management.

### APPLICATIONS

- ✓ Acid spearhead, stimulation and workover treatments
- ✓ Enables spotting of spearhead acid with the perforating guns (patented formulas and methods)
- ✓ Low to high temperature wellbore conditions

Enviro-Syn HCR-7000-WL is compatible with all coated and uncoated wireline cables currently available and manufactured in North America.

### PHYSICAL PROPERTIES

Appearance:	Amber liquid
Specific Gravity:	1.105
Odor:	Slight
Freezing Point:	≈ -50°C (-58°F) ≈ -20°C (-4°F) at 1:2 (HCR:water)
Boiling Point:	> 100°C (212°F)
pH:	< 1.0
Salinity:	≈ 32%
Solubility:	Soluble in water
Shelf Life:	> 1 year

### Outstanding HSE profile

- Non-corrosive to skin
- Low fuming\*
- Biodegradable
- Non-regulated for ground transportation (USDOT)

\*NOTE: Reduced immediate evolution of hydrogen chloride vapor at ambient temperature

### FEATURES & BENEFITS

- ✓ Aggressive reaction rate (spend nature) versus typical modified or synthetic acid systems for spearhead treatments
- ✓ Wireline compatible – custom blend allows spotting of acid with wireline and tools in hole
- ✓ Reduces frac spread pumping time (average 10 – 15 min/stage depending on well design) as ball and acid are at perforations
- ✓ Reduces water requirements by one hole volume per stage (average 30 – 50 m<sup>3</sup>/stage, 8,000 – 13,000 gal/stage depending on well design)
- ✓ Allows acid to be accurately spotted across all perforation clusters for optimal acid diversion and frac placement
- ✓ Adjust concentrations on the fly for zones with tougher breakdowns
- ✓ Minimal reprecipitation of scale at high pH levels
- ✓ Long-term casing and cable corrosion protection in case of delayed events
- ✓ No degradation of wireline coating or jacket
- ✓ Compatible with typical elastomers used in oil and gas (e.g., Viton, Nitrile and EPDM)
- ✓ High stability in solution
- ✓ Blends available up to 150°C (302°F)

## TOTAL SOLUBILITY

Table 1. Total solubility of Enviro-Syn HCR-7000-WL on a variety of scales.

Acid	Scale	Total Solubility (kg/m <sup>3</sup> )	Total Solubility (lb/gal)
15% HCl	CaCO <sub>3</sub>	211	1.76
HCR-7000-WL Concentrate	CaCO <sub>3</sub>	216	1.80
HCR-7000-WL Concentrate	CaMg(CO <sub>3</sub> ) <sub>2</sub>	190	1.59
HCR-7000-WL Concentrate	FeS	170	1.42

NOTE: High temperature corrosion inhibitor loadings can alter total solubilizing ability.

## CORROSION RATES

With ultra-low metal corrosion properties, Enviro-Syn HCR-7000-WL has corrosion rates well below oilfield industry accepted values on typical oilfield alloys.

Table 2. Corrosion rates of Enviro-Syn HCR-7000-WL blends.

Blend (HCR:water)	Temp (°C /°F)	Coupon	Time (hr)	Corrosion (mm/yr)	Corrosion (lb/ft <sup>2</sup> )
1:2	110 / 230	316SS	6	10.413	0.011
1:2	110 / 230	P-110	6	1.557	0.002
1:2	110 / 230	L-80	6	2.199	0.002
1:2	110 / 230	J-55	6	1.398	0.002
1:2	110 / 230	QT-1100	6	3.724	0.002

NOTE: Oilfield industry typically accepts a corrosion rate less than 0.050 lb/ft<sup>2</sup> at 6 hours. Coiled tubing typically accepts a corrosion rate less

Table 3. Corrosion rates with a 1:2 (HCR:water) Enviro-Syn HCR-7000-WL blend on wireline coupons.

Blend (HCR:water)	Temp (°C /°F)	Coupon	Time (hr)	Weight Change (g)	Weight Change (%)	Breaks in Strands
1:2	110 / 230	Triple Strand Wireline	4	0.5195	2.94	0
1:2	110 / 230	Triple Strand Wireline	5	0.4472	2.55	0
1:2	110 / 230	Greased Wireline	6	1.2817	6.04	0
1:2	110 / 230	Greased Wireline	10	1.3921	6.62	0
1:2	110 / 230	Greased Wireline	12	1.9431	9.11	0
1:2	110 / 230	Greased Wireline	72	1.2054	5.41	0

NOTE: Oilfield industry typically accepts a corrosion rate less than 0.050 lb/ft<sup>2</sup> at 6 hours. Coiled tubing typically accepts a corrosion rate less than 0.020 lb/ft<sup>2</sup> at 6 hours.

### WIRELINE TESTING

Enviro-Syn HCR-7000-WL has been extensively tested with major wireline suppliers' equipment.

Table 4. Tensile breaking force of wireline treated with Enviro-Syn HCR-7000-WL blends.

Blend (HCR:water)	Coupon	Temp (°C /°F)	Time (hr)	Tensile Breaking Force (N / lbf)	% Retained (vs control)
Control	Greased Wireline	N/A	N/A	1777 / 399	N/A
Control	Exterior (Triple Strand)	N/A	N/A	1167 / 263	N/A
Control	Interior (Single Strand)	N/A	N/A	2442 / 549	N/A
1:2	Exterior (Triple Strand)	110 / 230	4	1097 / 247	94%
1:2	Interior (Single Strand)	110 / 230	4	2240 / 130	92%
1:2	Exterior (Triple Strand)	110 / 230	5	995 / 224	85%
1:2	Interior (Single Strand)	110 / 230	5	2395 / 538	98%
1:2	Greased Wireline	110 / 230	6	1669 / 375	94%
1:2	Greased Wireline	110 / 230	10	1544 / 347	87%

### SAFETY, STORAGE & HANDLING

- ✓ Stored in sealed containers, such as plastic pails, lined drums and HDPE IBC totes
- ✓ Fittings and valves should be HDPE, brass or stainless steel
- ✓ If heating, use a stainless-steel heat exchanger or tank steam coils, keeping the temperature below 65°C (150°F)
- ✓ Shelf life of > 1 year; confirm corrosion if product sits for > 60 days
- ✓ Consult SDS for additional information and PPE requirements

Talk to us today about our revolutionary products available globally.

[info@fluidenergygroup.com](mailto:info@fluidenergygroup.com) or [www.fluidenergygroup.com](http://www.fluidenergygroup.com)

The Fluid logo, Enviro-Syn, HCR-7000-WL and Modified Acid are trademarks or registered trademarks of Fluid Energy Group Ltd., in Canada and other countries. To the best of our knowledge, the information contained herein is accurate and reliable; however, we provide no guarantees or warranties, express or implied, and we do not assume any liability for the accuracy or completeness of such information, as conditions and methods for use are beyond our control. Some or all of the products or methods discussed herein may be covered by one or more patents or patents pending. No freedom from infringement of any patent owned by us or others is to be inferred. © 2022, Fluid Energy Group Ltd.

14-SEP-2022